
DATA SHEET

Semi-rigid Cryogenic Cable, 50 Ohm, up to 40 GHz, Ø0.86 mm, Beryllium Copper, bent

SR_34_BC_02_bent

Properties

- Low loss at cryogenic temperatures for stable RF performance down to 4K.
- Ultra-low thermal conductivity (50 * 10^-6 Wcm/k) minimizes heat transfer.
- High-frequency capability up to 40 GHz in a slim Ø0.86 mm cable design.



Construction			
Component	**Material**	**Detail**	**Diameter**
Centre conductor	Copper Beryllium Alloy	Wire	0.2 mm +/- 0.01 mm
Dielectric	PTFE (Polytetrafluoroethylene)	95%	0.66 mm +/- 0.026 mm
Outer conductor	Copper Beryllium Alloy	Tube	0.86 mm +/- 0.05 mm

Electrical data	
Impedance	50 Ω
Operating frequency	≤ 40 GHz
Capacitance	76.7 pF
Velocity of signal propagation	77 %
Signal delay	4.622 ns/m @ 10 GHz
Screening effectiveness	> 100 dB at frequency 5 GHz ... 20GHz
Inner conductor resistance	2.8 Ω/m @ 300 K
Outer conductor resistance	0.3 Ω/m @ 300 K
Insertion Loss at 300 K (26.85 °C)	3.9 dB/m / 1 GHz
	11.5 dB/m / 10 GHz
	16.5 dB/m / 20 GHz
	23.5 dB/m / 40 GHz
	28 dB/m / 60 GHz
Insertion Loss at 10 GHz	11.5 dB/m @ 300.00 °K (26.85 °C)
	11.3 dB/m @ 110.00 °K (-163.15 °C)
	11 dB/m @ 77.00 °K (-196.15 °C)
	10.8 dB/m @ 20.00 °K (-253.15 °C)
	10.5 dB/m @ 4.00 °K (-269.15 °C)

Mechanical data	
Weight	approx. 4 g/m
Static bending radius	≥ 3.2 mm

Semi-rigid Cryogenic Cable, 50 Ohm, up to 40 GHz, Ø0.86 mm, Beryllium Copper, bent

SR_34_BC_02_bent

Environmental data	
Thermal conductivity at 4K	50 * 10-6 W·cm/K
Heat quantity at 4k - 20K	28 µW/K
Heat quantity at 4k - 100K	94 µW/K

Material compliance			
Item number	Directive / Regulation	Rating	Exemptions / Details
85276569	RoHS 2011/65/EU and (EU) 2015/863	Compliant without exemption	
	REACH 1907/2006 Article 33 SVHC	Free of SVHC >0,1%	
85276570	RoHS 2011/65/EU and (EU) 2015/863	Compliant without exemption	
	REACH 1907/2006 Article 33 SVHC	Free of SVHC >0,1%	

Ordering information	
Item number	Item description
85276569	SR_34_BC_02_bent_300
85276570	SR_34_BC_02_bent_450

HUBER+SUHNER is certified by ISO 9001, ISO 14001, ISO 45001, IATF 16949, AS/EN 9100 and ISO/TS 22163-IRIS. Waiver: Facts and figures herein are for information only and do not represent any warranty of any kind.
DOCUMENT PIM-P61799 / Date of publication: 10.11.2026 / uncontrolled copy